

Sika® Separol 180C

Chemical Form Release Agent

Description	Form release agent in concentrated emulsion form
Uses	Form release agent for steel and wooden formwork. Sika® Separol 180 C facilitates removal and cleaning of shuttering. It shall be diluted with water prior to use
Advantages	<ul style="list-style-type: none"> ■ Easy to apply ■ Combined chemical and physical action ■ Ensures fair faced concrete finish ■ No staining <p>Suitable also for use on formwork used in steam curing process</p>
Technical Data	
Form/ Colour	Liquid / Yellowish
Density	~ 0.86 kg/ltr
Storage	Dry, cool, shaded place (max. +30 °C).
Shelf life	Min. 12 months if stored properly in unopened, original packaging
Packaging	20 ltr pail 200 ltr drum
Application	
Surface preparation	All surfaces to be coated with Sika® Separol 180C must be clean and free from grease and old concrete.
Application	<p>Dilute one litre Sika® Separol 180C with five litres of water (can be extended up to eight litres of water for some cases – pre-trial recommended) and stir thoroughly until the mixture turns into uniform milky solution.</p> <p>Apply one uniform coat of Sika® Separol 180C by brush, roller or spray equipment, on dry or damp formwork.</p> <p>The dilution should be re-stirred immediately prior to use.</p>
Cleaning	Clean all tools and equipment with water
Remarks	Protect coated formwork from rain. Cleaning the mould surface between each use and before application is essential to prevent the formation of hardened concrete "build up".
Precautionary measures	<p>Wear suitable protective clothing, goggles and gloves during working with this product.</p> <p>The product should not get into drains, water and ground.</p>



Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the product when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



PT. Sika Indonesia
Jl. Raya Cibinong- Bekasi km. 20
Limusnunggal- Cileungsi
BOGOR 16820 - Indonesia
Tel. +62 21 8230025
Fax +62 21 8230026
Website : www.sika.co.id
e-mail: sikacare@id.sika.com

Branches
Surabaya :
Puri Niaga Blok G No. 29, Jl. Raya Rungkut Menanggal 11, Surabaya
Tel : 031-8690202 ; Fax : 031-8682123
Medan :
Jl. Pancing / Jl. Willem Iskandar No.75 & 75 A, Kec. Medan Tembung
Tel : 061- 6619500; Fax : (061) 6619400
Batam :
Jl. Laksamana Bintan, Komp. Bumi Riau Makmur Blok E No.3, Sungai Panas
Tel : (0778) 424928; Fax : (0778) 450189

